








ネジの強度及び鉄板下地に対する保持力

1 N=0.102 kgf

		ドリルポイントネジ <ネオタップ>								
		品 種		S W C H 1 8 A					S U S 4 1 0	
		材 質								
		呼び径 mm		3.5	3.9	4.2	4.8	6.0	3.9	4.2
ドリル径 mm		2.8	3.1	3.4	4.3	5.3	3.0	3.3		
 ねじり強さ (N・m) 			4.21	5.88	7.06	11.27	21.56	5.59	6.66	
	 引張力 (N) 			5,635	7,742	9,624	12,691	16,611	7,497	9,153
		 剪断力 (N) 			4,763	6,537	7,487	8,516	17,003	6,419
引抜き保持力 (N) 	試験材厚さ mm		1.2	1,333	1,588	1,666	—	—	480	1,578
		1.6	2,538	2,822	2,900	—	—	2,764	2,695	
		2.3	4,880	5,370	5,557	5,841	7,448	5,312	5,508	
		3.2	—	—	8,497	8,781	10,016	—	8,281	
		4.5	—	—	—	11,368	13,916	—	—	
		6.0	—	—	—	—	17,297	—	—	